USSN:09/886,646 Response to Office Action dated September 30, 2005 Atty Docket: 620-010334-US (PAR) Page 8

III. CLAIM AMENDMENTS

- 1. (Currently Amended) Light-refracting, color-enhancing consisting essentially of mixture a of (a) pelletized microparticles of rubber having a diameter up to about 150μ and (b) transparent or translucent glass plastic beads having a diameter up to about 20 $\frac{70\mu}{}$ and (c) a resinous binder material which cures to form a hard, translucent, lightrefracting paint layer.
- 2. (Currently Amended) A coating composition according to claim 1 in which the beads have a maximum diameter within the range of about 10 to 20 microns.
- 3. (Currently Amended) A coating composition according to claim 2 in which the maximum diameter is between 12 and 18 microns.
- 4. (Currently Amended) A coating composition according to claim 1 in which the beads are clear glass and have a refractive index between about 1.5 and 2.5.
- 5. (Currently Amended) A coating composition according to claim 4 in which the refractive index is between about 1.9 and 2.1.
- 6. (Currently Amended) A coating composition according to claim 4 in which the glass beads comprise a mixture of beads having different refractive indexes.

USSN:09/886,646 Response to Office Action dated September 30, 2005 Atty Docket: 620-010334-US (PAR) Page 9

- 7. (Currently Amended) A coating composition according to claim 1 in which the pelletized rubber particles have a diameter [[up to]] of about 150μ 120μ .
- 8. (Currently Amended) A $\frac{1}{1}$ composition according to claim 1 in which the pelletized rubber content is between about 2% and 40% by weight.
- 9. (Currently Amended) A coating composition according to claim 1 in which the binder material comprises a mixture of a prepolymer having reactive sites, and a poly-functional crosslinking agent which is reactive with said sites to cure the binder material.
- 10. (Currently Amended) A coating composition according to claim 1 comprising a paint coating in which the resinous binder material contains a volatile solvent or vehicle which is evaporated to dry the coating below the baking temperature of the paint composition.
- 11. (Currently Amended) A coating composition according to claim 10 in which the volatile solvent is an organic solvent, and the coating composition has a solids content above about 60%.
- 12. (Currently Amended) A coating composition according to claim 10 in which the volatile vehicle is water.
- 13. (Currently Amended) A coating composition according to claim 1 in which the glass bead content is between about 10-20% by weight of the composition.

USSN:09/886,646 Response to Office Action dated September 30, 2005 Atty Docket: 620-010334-US (PAR) Page 10

- 14. (Withdrawn) Process for applying a light-refractive, colorenhancing coating to a substrate comprising the steps of (1) spraying said substrate with a coating composition comprising (a) at least 2% by weight of pelletized rubber and (b) at least about 10% by weight of transparent or translucent glass beads having a diameter up to about 70μ and (c) a curable resinous binder material; (2) heating the coating, if necessary to evaporate any volatile solvent or vehicle, and (3) drying the coating to cure the resinous binder material and form a light-refracting coating containing the pelletized rubber and the glass beads which refract, scatter and dissipate applied light within the cured coating and which is firmly bonded to said substrate.
- 15. (Withdrawn) Process according to claim 14 in which the pelletized rubber particles have a diameter up to about 150 microns.
- 16. (Withdrawn) Process according to claim 14 in which the pelletized rubber content is up to about 40% by weight of the solids content.
- 17. (Withdrawn) Process according to claim 14 in which the pelletized rubber content is between about 5% and 20% by weight of the solids content.